



Jowat® 950.20



UF resin for classic veneering and flat lamination

Powder form for easy transport and storage

Low formaldehyde E1 bonding (according to DIN EN 717-2)

For furniture and furnishings

Wood-based material lamination is one of the most important applications for all types of adhesives in the standard production of furniture. The range of bonding products is constantly expanded, for instance with thermoplastic hot melt adhesives, liquid dispersion glues and reactive hot melts based on polyurethane (PUR). In the field of thermosetting adhesives based on polycondensation resins, urea formaldehyde resin glues (UF resins) are the most significant group of products. They are widely used in the general production of furniture due to major benefits such as low manufacturing costs, short setting times (hardening), and high bond strengths.

Jowat® 950.20 is a UF resin for hot curing, especially for classic veneering and for flat lamination with pressure laminates such as HPL (High Pressure Laminates) or CPL (Continuous Pressure Laminates). Due to an integrated hardener, the formaldehyde glue is prepared by simply mixing the powder with water (mixing ratio by weight powder : water 2:1).

Bonds with **Jowat® 950.20** meet the requirements for class I according to DIN EN 314-2 and E1 according to DIN EN 717-2.

Benefits

- ✓ **Efficiency.** The powder form of the adhesive provides a major advantage in countries with extreme climatic conditions (very cold or very hot). The glue is prepared shortly before processing depending on the local need. This facilitates a safe transport and storing of the adhesive.
- ✓ **Versatility.** For a more elastic glue line with improved adhesion (e.g. for difficult-to-bond veneers), the adhesive can be mixed with 10 – 20 % of PVAc dispersion (for instance **Jowacoll® 113.10**).
- ✓ **Low in formaldehyde.** **Jowat® 950.20** facilitates an E1 bond quality (according to DIN EN 717-2).

Jowat® 950.20

UF resin for bonding veneer, decor papers and pressure laminates (HPL, CPL) to wood-based substrates. For warm and hot presses, as well as for the manufacture of plywood form parts in high-frequency presses.

Base polymer		urea formaldehyde resin (UF)
Bulk density	[g/l]	approx. 610 (powder)
Resin content	[%]	approx. 68
Appearance		beige
Pot life at 20 °C	[h]	< 7
Open time	[min]	approx. 13
Minimum pressing temperature	[°C]	approx. 70
Supply form		powder

INFO-BOX | Pressing

Pressure [N/mm²]	> 0.2			
Pressing temperature [°C]	70	80	100	120
Minimum pressing time [min]	5	3	1	0.5

The information given in this leaflet is based on test results from our laboratories as well as on experience gained in the field, and does in no way constitute any guarantee of properties. Due to the wide range of different applications, substrates, and processing methods beyond our control, no liability may be derived from these indications nor from the information provided by our free technical advisory service. Before processing, please request the corresponding data sheet and observe the information in it! Customer trials under everyday conditions, testing for suitability at normal processing conditions, and appropriate fit-for-purpose testing are absolutely necessary. For the specifications as well as further information, please refer to the latest technical data sheets.