

Door manufacture

- Efficient adhesive systems for all requirements
- Dispersion and hot melt adhesives free of formaldehyde
- Polyurethane adhesives for highest qualities



Jowacoll® 103.30
Jowacoll® 148.00
Jowatherm-Reaktant® 609.30
Jowatherm® 280.50
Jowat-Toptherm® 236.70

Door manufacture with Jowat adhesives



Doors are elements that increasingly serve to add value to the interior of homes. The variations in product and design, areas of use, and technical demands, result in an almost endless variety, and in consequence broaden the requirements which the manufacturers have to meet. The range covers plain doors for interior uses, high-end solid wood doors, and conventional doors assembled of casing and panels. The possible combinations of door panels and door frames lead to a complex and nearly infinite variety of products. Apart from the high technical standards that doors for home interiors have to meet, the requirements for office and institutional uses are constantly becoming more stringent. Fire protection, soundproofing, and safety systems, are matters that must be taken into account in the construction of doors.

From individual doors manufactured in small shops, to high numbers in industrial serial production - all manufacturing techniques require adhesives adapted to the respective process, while ease of handling, low in emissions, and high efficiency is expected as well. It goes without saying that the bond also has to match the quality standard expected from the finished door when installed in the location of use.

Whether finishing the surfaces of wood-based panels by using decor pressure laminates like HPL or CPL or for the conventional veneer surfaces:

Jowacoll[®] PVAc dispersion adhesives can be used reliably in stationary or in continuous manufacturing processes.

To apply decor paper or thermoplastic foils in industrial-scale laminating lines, **Jowacoll**[®] foil adhesives with superior adhesion properties are tried and proven products.

In industrial serial manufacture of door panels, the demand for higher cycle rates is constantly increasing. Jowat hot melt adhesives facilitate sequences where pressing times have been reduced to a minimum. Manufacturing with conventional EVAs or modern polyolefin hot melt (PO) adhesives is reliable and highly efficient.

Highest levels of moisture and heat resistance can be reached by using polyurethane hot melts from the family of **Jowatherm-Reaktant**[®] adhesives.

Finishing the edges of door panels can be carried out with the most diverse edgebands: Straight edges, softformed, or the conventional fold edge. For all these processes, just like for the wrapping of door frames, Jowat AG is supplying a complete range of hot melt adhesives based on EVA, PO, and PUR, satisfying all demands of a modern and highly efficient door production.

Jowacoll® 103.30

Durability class		D3
Viscosity	[mPas]	approx. 12,000
Solid content	[%]	approx. 48
pH value		approx. 3.0
Crosslinking Agent (optional)		Jowat® 195.40

PVAc dispersion adhesive for flat lamination of wood-based substrates with decor foils, HPL, CPL or thermoplastic foils.

Jowacoll® 148.00

Density	[g/cm³]	approx. 1.35
Viscosity	[mPas]	approx. 13,000
Solid content	[%]	approx. 70
pH value		approx. 7.0
Crosslinking Agent (optional)		Jowat® 195.40

Foil adhesive for lamination of wood-based substrates with decor foils, especially with thermoplastic foils (e. g. PVC).

Jowatherm-Reaktant® 609.30

Density	[g/cm³]	approx. 1.1
Viscosity at 120 °C	[mPas]	approx. 16,000
Processing temperature [°C]		approx. 110 – 130
Reaction time	[d]	approx. 3 (depending on ambient conditions)

PUR hot melt adhesive for lamination of wood-based substrates with decor foils, HPL, CPL or thermoplastic foils.

Jowatherm® 280.50

Density	[g/cm³]	approx. 1.1
Viscosity at 200 °C	[mPas]	approx. 80,000
Processing temperature [°C]		approx. 180 – 200
Softening range	[°C]	approx. 95

EVA hot melt adhesive for edgebanding (straight or folded), and for softforming applications.

Jowat-Toptherm® 236.70

Density	[g/cm³]	approx. 0.89
Viscosity at 190 °C	[mPas]	approx. 26,000
Processing temperature [°C]		approx. 180 - 200
Softening range	[°C]	approx. 110

PO hot melt adhesive for wrapping of profiles or door frames made of solid wood, particleboard or MDF, with decor paper, CPL, thermoplastic foils or fleece-backed veneers.



Jowat | Ihr Partner in Sachen Kleben

Jowat | Your Partner in bonding



The information given in this leaflet is based on test results from our laboratories as well as on experience gained in the field, and does in no way constitute any guarantee of properties. Due to the wide range of different applications, substrates, and processing methods beyond our control, no liability may be derived from these indications nor from the information provided by our free technical advisory service. Before processing, please request the corresponding data sheet and observe the information in it! Customer trials under everyday conditions, testing for suitability at normal processing conditions, and appropriate fit-for-purpose testing are absolutely necessary. For the specifications as well as further information, please refer to the latest technical data sheets.

Jowat – Kleben erster Klasse
Jowat – first class bonding

www.jowat.com

Jowat 
Klebstoffe

Australia Brasil Canada Chile 中国 Colombia Deutschland France Italia Malaysia Mexico Nederland Polska Россия
Sverige Suisse ประเทศไทย Türkiye United Kingdom United States of America دوحتملا ءيبرعلا تارامالا Việt Nam