



Jowatherm-Reaktant®

609.00



Powerful PUR hot melt adhesives for flat lamination


- Very wide range of adhesion; for many materials
- High initial strength; for high-tension substrates
- Stringing-free and processor-friendly

The adhesive for challenging conditions

Jowatherm-Reaktant® 609.00 is renowned in the furniture and building element industry for its problem-solving capabilities in laminating processes. This high-performance adhesive continues to impress when other products have reached their limits. The high initial strength facilitates the bonding of high-tension materials while also allowing for a repositioning of the substrate before the parts are pressed together. Coupled with the broad spectrum of adhesion, it ensures a reliable bonding of a wide range of substrates—not only wood-based materials but also metal and other challenging surfaces. The adhesive can be applied without stringing at feed speeds of up to 40 m/min.

Jowatherm-Reaktant® 609.00

Powerful PUR hot melt adhesive for the flat lamination of wood-based materials

Based on		PUR
Viscosity	at 120°C	~15,000 mPas
Processing temperature		110°C–130°C
Open time	at 120°C	~4 min
Initial strength		● ● ●
Range of adhesion		● ● ●
Certification		 IMO Resolution A.1/3.18 e

After bonding, clean the rollers easily and thoroughly with the matching Jowat® cleaner.



Cleaning agent for roller applicator systems

	Jowat® 930.23	Jowat® 930.22	Jowat® 930.27
Supply form	powder	powder	pastilles
Geographic region	EMEA	AMER	APAC

The information given in this leaflet is based on test results from our laboratories as well as on experience gained in the field, and does in no way constitute any guarantee of properties. Due to the wide range of different applications, substrates, and processing methods beyond our control, no liability may be derived from these indications nor from the information provided by our free technical advisory service. Before processing, please request the corresponding data sheet and observe the information in it! Customer trials under everyday conditions, testing for suitability at normal processing conditions, and appropriate fit-for-purpose testing are absolutely necessary. For the specifications as well as further information, please refer to the latest technical data sheets.