

2-component PUR adhesive (resin component)

688.30

Application: Two-component adhesive for small and large industrial applications and small shops. Bonding and fixing of various types of wood, plywood, particleboard, mineral fibreboard panels, metals like iron, galvanized iron plate, aluminium etc, fibre-reinforced polyester, foamed plastics like expanded polystyrene, PVC and plastic honeycombs.

Characteristics/ Directions for Use: Free of formaldehyde. Tough-hard 2-component adhesive with very good resistance data to low and high temperatures, to humidity and ageing. Stir up the resin component every time before use. The adhesive may be applied by hand or with a 2-component dosing and mixing unit. The resin component is mixed with the hardener Jowapur® 688.99

Mixing ratio:	Resin	:	Hardener
	688.30	:	688.99
Parts by weight:	4.5	:	1
Colour of the mix:	beige		
Foaming:	-		
Processing temperature [°C]:	10 - 50		
Pot life at +20 °C [min]:	25 – 35		
Open time at +20 °C [min]:	20 – 30		
Pressing time at +20 °C [min]:	120 – 150		
Pressing time at +40 °C [min]:	60		
Final strength reached in [d]:	6 – 7		
Temperature resistance [°C]:	-40 to +90 (short-term up to +130 °C)		

Please protect the press with a suitable Jowat® separating agent for PUR adhesives and release paper to prevent the press from gluing shut. The properties of the materials and the processing conditions will influence the results. Customer trials are therefore recommended.

Technical Data: Compound viscosity at +20 °C [mPas]: approx. 6,000 (Brookfield)
 Density at +20 °C [g/cm³]: approx. 1.4
 Solid content Resin + Hardener [%]: approx. 98 ± 2

continued on page 2

01/17 All data indicated are characteristics represented as average values. Our technical data sheets are constantly revised to represent the latest state of technology. This edition is replacing all previous ones, and is valid on the date of compilation.
Please refer to the last page of this data sheet for additional information.



- Cleaning:** Before curing the prepolymer can be cleaned with a solvent-soaked rag for instance using Jowat® Thinner 401.30 or with Jowat® PUR Cleaner 402.38, after curing only mechanical removal (emery paper).
- Storage:** In properly closed containers, cool and dry (15 – 25 °C). Best-before date, please refer to label on the packaging unit.
- Packaging:** Types of packaging and units upon request.
- Remarks:** For further information concerning handling, transport and disposal, please refer to the Safety Data Sheet.
Our information on this data sheet is based on test results from our laboratories as well as on experience gained in the field by our customers. It can, however, not cover all parameters for each specific application and is therefore not binding for us. The information given in this leaflet represents neither a performance guarantee nor a guarantee of properties, nature, condition, state or quality. No liability may be derived from these indications nor from the recommendations made by our free technical advisory service.

Jowat Information

Gluing as one of the most efficient methods of bonding is constantly gaining importance and expanding into new areas of application. At the same time, the number of substrates to be bonded is also growing at an unprecedented rate. New methods and equipment to process adhesives are developed.

The in-house R & D departments of Jowat are responding with intensive efforts to keep pace with these constant changes. A highly qualified team of chemists and engineers is using the latest techniques and brightest ideas to provide the utmost in advice our customers and to make sure that they get the adhesive which meets their needs.

Our information is based on test results from our laboratories as well as on experience gained in the field by our customers. This advice, however, cannot cover all eventualities for each specific application and as such is not binding for us. Please, contact our technical service department in each case to find out what the actual technical state of development for the respective product is, and request the latest data sheet. Any use of our product without this precautionary measure would be your sole responsibility.

The processing company itself must therefore test the adhesives manufactured by us for suitability in each individual case. This applies to the first use of a sample as well as to modifications during an ongoing production.

We are therefore requesting all our new customers to test our adhesives for suitability on original parts at conditions equal to normal processing conditions. The bond has then to be subjected to the actual stress which it would undergo when in use and has to be assessed. This test is absolutely necessary.

Customers who undertake modifications during a running production are requested to pass this information on to us. Please notify us when machines are set to new parameters as well as when the substrates to be bonded are changed. Only then will Jowat be able to provide our most up-to-date information to the processor using our adhesives.

The information given in this leaflet is based on practical experience and on results of tests in our laboratory, and does in no way constitute any guarantee of properties. No liability may be derived from these indications nor from the recommendations made by our technical advisory service.