

2K Epoxy Resin

692.30

Application: Highly resistant, durable construction adhesive for bonding steel rods, for repair work and filling of cracks in wood. Can also be used for bonding many other materials, for example metals, concrete, stone and EPS / expanded polystyrene.

Basis: Epoxy resin and amine hardener.

Characteristics/ Directions for Use: When used correctly, the steel rods inserted with Jowat® 692.30 will achieve the minimum values according to the DIN EN 1995-1-1/NA for pull resistance. Please observe the relevant technical documentation for the insertion and dimensioning of steel rods. Heat resistance approx. 100 °C. For interior and exterior applications.

The surfaces to be bonded have to be clean, dry and grease-free. Application is carried out using a 2-component cartridge with a static mixer (at least 18 to 24 elements). A suitable type of gun would be a squeeze out piston type for cartridges, which can be operated manually or by electronic controls. We do not recommend using guns operating with compressed air, since the air jet exerts uncontrolled pressure on both chambers, and this may prevent a homogenous mixing result. Larger quantities can also be mixed homogeneously in a clean container and then applied e. g. with a toothed spatula within the pot life.

Alternatively, it is also possible to use automatic 2-component dosing units.

The adhesive may be applied to one or both surfaces.

Since the adhesive works like a casting compound, no pressure is needed for a complete cure. However, it may be necessary to immobilize the substrates at low to medium pressure.

Technical Data:	Component A 692.31	Component B 692.32
Appearance:	beige	beige
Density [g/cm³]: (Jowat test method)	approx. 1.42	approx. 1.54
Solids content [%]: (Jowat test method)	approx. 100	approx. 100
Mixing ratio [by volume]:	2	1
Mixing ratio [by weight]:	100	50

Data of the mixture

Appearance:	beige
Minimum processing temperature [°C]:	>10
Final strength after [h]:	>24
Processing time [min]:	approx. 35
Curing at 20 °C [h]:	handling strength after approx. 3 full strength after approx. 24
Fast curing at 80 °C [h]:	approx. <1
Shore hardness D at 20 °C:	approx. 85
Tensile strength [MPa]: (following DIN EN ISO 527)	approx. 48
Tensile strain at break [%]: (following DIN EN ISO 527)	approx. 1.40
Temperature resistance [°C]:	-40 up to 120 (short-term higher)

continued on page 2

01/24 All data indicated are characteristics represented as average values. Our technical data sheets are periodically revised to represent the latest state of technology. This edition is replacing and superseding all previous ones, and is valid on the date of compilation.
Please refer to the last page of this technical data sheet for additional information.

Jowat 
Klebstoffe

**Requirements
for a
High-Quality
Bonding
Process:**

The properties (e.g. surface tension, plasticizer content...) and the conditioning of the substrates, as well as the processing conditions (e.g. ambient temperature, humidity...) will influence the processes of joining and bonding. Customer tests under consideration of everyday production conditions are therefore absolutely necessary to define stable process parameters and to ensure that the product is fit for purpose. For best bonding results, the materials to be bonded should be free of dust, oil, and grease, and be dry. Ideally, the minimum temperature should be at 18 °C. Avoid draft.

Our Application Technology Department and our Application Specialists will provide technical data to assist you in your choice of an appropriate product for your requirements. Please observe the information in the section "Remarks."

As a suggestion on how to establish high-quality bonding processes, please refer to DIN 2304.

Specification:

**Component A
692.31**

**Component B
692.32**

Viscosity at 20 °C [mPas]:
(Brookfield, spindle 7, 20 rpm)

47,500 ± 22,500

47,500 ± 22,500

data of the mixture:

Pot life / Processing time [min]:
(Jowat test method)

30 ± 5

Thinning:

May not be thinned.

Cleaning:

Before curing the prepolymer can be cleaned with a solvent-soaked rag for instance using Jowat® Thinner 401.30, after curing only mechanical removal (e.g. emery paper).

**Storage/
Transport:**

The product should remain stored in properly closed original containers, dry and cool (15 – 25 °C). Do not transport at temperatures below +5 °C.

For best-before date, please see container label.

After the elapse of the best-before date, it is essential that you again verify that the product is fit for your intended application.

Packaging:

180 ml / 260 g cartridges (like standard silicone cartridges). 400 ml / 580 g side-by-side cartridges. Both components are also available in 25 l hobbos or 200 l drums.

Information about other types of packaging and units is available upon request.

Remarks:

For further information concerning safety, handling, transport and disposal, please refer to the safety data sheet.

The information on this data sheet is based on test results from our laboratories as well as on reported experience gained in the field by our customers. It can, however, not cover all parameters for each specific application and is therefore not binding upon Jowat, nor should it be relied upon in lieu of your own required testing. The information given in this leaflet does not represent a performance guarantee. Unless otherwise agreed with our customers, the values stated in the section "Specification" shall be regarded as the finally agreed upon product properties. No liability may be derived from the information contained herein nor from the information provided by our free technical advisory service.

Jowat Information

Gluing as one of the most efficient methods of bonding is constantly gaining importance and expanding into new areas of application. At the same time, the number of substrates to be bonded is also growing at an unprecedented rate. New methods and equipment to process adhesives are developed.

The in-house R & D departments of Jowat are responding with intensive efforts to keep pace with these constant changes. A highly qualified team of chemists and engineers is using the latest techniques and brightest ideas to provide the utmost in advice our customers and to make sure that they get the adhesive which meets their needs.

Our information is based on test results from our laboratories as well as on experience gained in the field by our customers. This advice, however, cannot cover all eventualities for each specific application and as such is not binding for us. Please, contact our technical service department in each case to find out what the actual technical state of development for the respective product is, and request the latest data sheet. Any use of our product without this precautionary measure would be your sole responsibility.

The processing company itself must therefore test the adhesives manufactured by us for suitability in each individual case. This applies to the first use of a sample as well as to modifications during an ongoing production.

We are therefore requesting all our new customers to test our adhesives for suitability on original parts at conditions equal to normal processing conditions. The bond has then to be subjected to the actual stress which it would undergo when in use and has to be assessed. This test is absolutely necessary.

Customers who undertake modifications during a running production are requested to pass this information on to us. Please notify us when machines are set to new parameters as well as when the substrates to be bonded are changed. Only then will Jowat be able to provide our most up-to-date information to the processor using our adhesives.

The information given in this leaflet is based on practical experience and on results of tests in our laboratory, and does in no way constitute any guarantee of properties. No liability may be derived from these indications nor from the recommendations made by our technical advisory service.